



DOWN RIVER LLC

Where Quality is Found.

Rigid-Cor & Hardboard Physical Properties

	Rigid-Cor		Standard Hardboard		Tempered Hardboard	
	1/8"	5.3mm	1/8"	5.3mm	1/8"	5.3mm
Thickness	1/8"	5.3mm	1/8"	5.3mm	1/8"	5.3mm
Density	59 lb	55 lb	56.2-68.7 lb	55 lb	59 lb	57-65 lb
Internal Bond	260 psi	261 psi	171 psi	90 psi	171 psi	130 psi
Moisture Content	7%	8.00%	4-8.5%	8%	4-8.5%	8%
Thickness Swell	29%	12%	20%	20%	20%	15%
MOE	653,000 psi	653,000 psi	N/A	N/A	N/A	N/A
MOR	8000 psi	8400 psi	5800 psi	4500 psi	5900 psi	6000 psi
Weight/panel	19 lbs	32 lbs	21 lbs	35 lbs	21 lbs	35 lbs

For more information
please call:

1-800-633-3838

Fax: 541-751-1090

—————
Main Office &
Manufacturing Plant:

3090 Memorial Drive
Klamath Falls, OR 97601

www.downriverllc.com

